

Duplexné akosti

EN	ASTM		Typické chemické zloženie, %						Zvarovací pomocný materiál elektrody EN 1600
			C	N	Cr	Ni	Mo	Ostatní	
1.4162 ¹	S32101	LDX 2101 [®]	0,03	0,22	21,5	1,5	0,3	5 Mn	LDX 2101* alebo 22 9 3 NL
1.4362	S32304	2304	0,02	0,10	23	4,8	0,3	-	2304* alebo 22 9 3 NL
1.4462	S32205 ²	2205	0,02	0,17	22	5,7	3,1	-	22 9 3 NL
1.4501	S32760	4501	0,02	0,27	25,4	6,9	3,8	W	25 9 4 NL
1.4410	S32750	SAF 2507 [®]	0,02	0,27	25	7	4	-	25 9 4 NL

Preklad tabuľky:

Hot rolled plate (Quatro)	– quarto plech
Hot rolled strip/sheet (CPP)	– Pás / tenký plech valcovaný za studena (CPP)
Cold rolled strip/sheet	– Pás / tenký plech valcovaný za studena
Cold rolled narrow strip	– Úzky pás valcovaný za studena
Bar	– Tyč
Rod	– Drôt
Tube/pipe	– Rúry/potrubie
Fittings	– Armatúry, fittingy
DUPROF™. Profiles in high strenght stainless steel	– DUPROF™, profily z vysoko pevnej nerezovej ocelie

P	Hot rolled plate (Quatro)
H	Hot rolled strip/sheet (CPP)
C	Cold rolled strip/sheet
N	Cold rolled narrow strip
B	Bar
R	Rod
T	Tube/pipe
F	Fittings
D	DUPROF™, Profiles in high strength stainless steel